



**PPM15 AB EVA (A=EVA) Coex Non-Crosslinked Polypropylene Foam Typical Properties**

Standard Test		
Thickness		2 mm
Density	pcf	4
Tensile Strength	psi	
machine direction		175
cross machine direction		115
Elongation	%	
machine direction		70
cross machine direction		85
Tear Strength	pli	
machine direction		40
cross machine direction		25

Nominal values for PPM 15 AB EVA with co-extruded skins • Property testing per ASTM D 3575-08

**Characteristics and Typical Areas of Application**

<ul style="list-style-type: none"> <li>• Temperature resistance from -40°F to +265°F (-40°C to +130°C)</li> <li>• 100% recyclable and physiologically safe</li> <li>• High energy absorption</li> <li>• Resistance to most chemical agents (solvents, petrol and lubricants)</li> <li>• CFC-free</li> </ul>	<ul style="list-style-type: none"> <li>• High mechanical strength and elasticity</li> <li>• Good for lamination and thermoforming/compression molding</li> <li>• Low water absorption due to the closed cell structure</li> <li>• Application Areas: Automotive, Packaging, Insulation</li> </ul>
---	---

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 7600 Oakwood St. Ext. • Mebane, NC 27302  
 email: info.us@armacell.com • www.armacell.com  
 800-638-6312 • fax: 919-304-3847

© 2008 Armacell LLC

PPM15AB	01	10	08	NA	NA
---------	----	----	----	----	----

ALL ARMACELL FACILITIES IN NORTH AMERICA ARE ISO 9001:2000 OR ISO/TS
--

PropaCene® is a registered trademark of Armacell LLC